




# PARTICLE SIZE DISTRIBUTION

## Typical Particle Size Distribution HPX® ADIRONDACK® Garnet Abrasives



# PARTICLE SIZE DISTRIBUTION

## Typical Particle Size Distribution HPX® ADIRONDACK® Garnet Abrasives

Grade		50	65	80	85	120	150	220	230
<b>Recommended Nozzle</b>		.040"	.040"	.040"	.030"	.030"	.020"	.020"	.015"
<b>Minimum Nozzle</b>		.040"	.040"	.030"	.030"	.020"	.015"	.015"	.015"
Screen Size Tyler/US	Opening Micron/Inch	Percent by Weight							
28 / 30	600 / .0234	<1							
32 / 25	500 / .0197	2	1						
35 / 40	425 / .0165	25	6						
42 / 45	355 / .0139	40	26	5	1				
48 / 50	300 / .0117	22	23	19	10				
60 / 60	250 / .0098	8	19	26	13				
65 / 70	212 / .0083	3	13	21	14	2			
80 / 80	180 / .0070		7	17	13	14			
100 / 100	150 / .0059		3	7	18	29	1		
115 / 120	125 / .0049		2	5	17	28	19	5	<1
150 / 140	106 / .0041				7	15	39	21	8
170 / 170	90 / .0035				4	7	24	28	31
200 / 200	75 / .0029				3	5	12	22	29
250 / 230	63 / .0025						4	15	18
270 / 270	53 / .0021						1	5	6
325 / 325	45 / .0017							4	8

Particle size distributions are typical. Some variation exists. Columns may not add up to 100% due to rounding.

2018-06

